



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>F16L 9/133, 11/04, 11/12, 9/12</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/32974</b> <b>(43) International Publication Date:</b> 8 June 2000 (08.06.00)
<b>(21) International Application Number:</b> PCT/NL99/00724 <b>(22) International Filing Date:</b> 25 November 1999 (25.11.99) <b>(30) Priority Data:</b> 1010675 27 November 1998 (27.11.98) NL <b>(71) Applicant (for all designated States except US):</b> WAVIN B.V. [NL/NL]; Stationsplein 3, NL-8011 CW Zwolle (NL). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> GAIKEMA, Gjalt, Martinus [NL/NL]; De Aak 104, NL-7701 LC Dedemsvaart (NL). STOFFELSMA, Jan, Uilke [NL/NL]; Badhuisplein 42, NL-7772 XC Hardenberg (NL). KREMER, Marinus, Peter [NL/NL]; Wilhelminaplein 4, NL-7772 AH Hardenberg (NL). <b>(74) Agent:</b> IEMENSCHOT, J., A.; Exter Polak & Charlouis B.V., P.O. Box 3241, NL-2280 GE Rijswijk (NL).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>In English translation (filed in Dutch).</i>
<b>(54) Title:</b> THERMOPLASTIC MULTILAYER WATER TRANSMISSION TUBE  <b>(57) Abstract</b>  <p>In a water transmission tube made of a thermoplastic and having a wall comprising at least two layers, the outer layer consists of a polyolefin material and the inner layer consists of a thermoplastic which is admixed only with substances required for processing it and which as such has no bacterial growth-promoting activity. The inner layer preferably consists of a thermoplastic which is selected from the group consisting of polyvinyl chloride (PVC), chlorinated polyvinyl chloride (CPVC), thermoplastic polyurethane (PU), acrylonitrile-butadiene-styrene (ABS) and polyethylene terephthalate (PET), and is preferably less permeable to organic substances than the outer layer.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## Thermoplastic multilayer water transmission tube

The invention relates to a thermoplastic water transmission tube.

5 Thermoplastic water transmission tubes are in general use and in most cases are eminently satisfactory. Water transmission tubes may however give rise to the problem of growth of bacteria on the inside of the tube. This is because water companies are increasingly adopting the practice of  
10 treating prepurified water destined to be drinking water not with chlorine, but with ozone or with UV light, in combination with filtration through a sand bed. This results in a better taste of the water and smaller amounts of organic chlorine compounds in the water, which are considered problematic in  
15 terms of public health. It is now found, however, that in the case of water purified in this manner in tubes of certain materials, in particular polyolefin materials, the gradual fouling by bacteria proceeds more rapidly than in tubes made of other materials. Particularly in tubes of polyethylene (PE) and  
20 to a lesser extent in tubes of polypropylene (PP) and polybutylene (PB) is relatively rapid fouling by bacteria observed.

To overcome the problem of fouling by bacteria in tubes designed to transport water it has been proposed to provide the  
25 tube with an inner layer in which a bactericidal substance has been incorporated (see for example US-A-5332160). Given the toxicity of the added substances, these tubes are not suitable, however, for drinking-water lines.

It is further found that many organic substances such as  
30 solvents readily permeate the wall of a tube of a polyolefin material. As a result, the use of water transmission tubes of polyethylene, polypropylene or polybutylene in soil contaminated with such substances has drawbacks, since the water transported through the pipes can become polluted.

35 To overcome this problem it has been proposed that tubes to be used under such conditions be provided with a layer which is made of another material and is impermeable or at least much less permeable to the pollutants. Preferably, said layer is then applied to or near the outside. A known material for this

- 2 -

purpose is aluminium in the form of a thin foil.

Also known, for example from EP-A-0686797, are multilayer plastic tubes for the purpose of transporting (petro)chemicals, comprising an outer layer on the basis of a polyolefin and an inner layer on the basis of a thermoplastic polyester. EP-A-0686797 states that these tubes are also suitable for transporting drinking water if there is the risk of pollution by diffusion from the outside to the inside, for example if drinking water lines are laid down in contaminated soil. Bacterial growth is not discussed, however.

It is an object of the invention to provide a water transmission tube made of a thermoplastic, in particular of a polyolefin material and more particularly of polyethylene, polypropylene or polybutylene, which tube gives rise to less fouling by bacteria within the tube, the tube preferably being suitable for use even in moderately contaminated soil.

This object is achieved by a water transmission tube according to claim 1.

Preferred embodiments of the water transmission tube according to the invention are defined in claims 2 to 6 inclusive.

It should be noted that the thermoplastics used for the inner layer are not admixed with any additional substances which inhibit bacterial growth, but that these plastics as such, i.e. in the form in which they are customarily used, do not or virtually do not give rise to bacterial growth.

A water transmission tube according to the invention can be fabricated by coextrusion, and tube sections can readily be joined together by means of customary joining techniques. Possible examples are joints by means of (electro-)fusion sockets, sockets with rubber rings and even butt-fused joints. A water transmission tube according to the invention is flexible and therefore highly suitable in cases in which the tube has to be laid in bent and/or coiled form (indoors or service pipes).

Water transmission tubes according to the invention can be used in various fields, the construction of the tube depending on the field of application.

A first field of application is indoors to transport cold and hot water. In this case, the diameters of the tubes are

- 3 -

usually relatively small, in the order of magnitude of from 15 to 32 mm. Since for these tubes the permeability to organic substances does not matter, but only bacterial growth is of importance, a thin inner layer is sufficient, for example having a thickness of 0.1 mm. The tube material, i.e. the material of the outer layer, can be polyethylene (PE), especially cross-linked polyethylene, usually referred to as PEX, polypropylene (PP), especially the so-called "random copolymer", or polybutylene (PB). Suitable materials for the inner layer for this field of application are above all polyurethane (PU) and chlorinated polyvinyl chloride (CPVC), both materials retaining their good properties at elevated temperatures.

A second field of application relates to service pipes. In this field of application the external diameters of the tubes are usually in the range from about 32 to 63 mm. The tube materials suitable for this application are, above all, various types of polyethylene, be they HDPE, MDPE or LDPE, the material optionally being cross-linked. Particularly suitable for the inner layer for this cold-water application are polyurethane (PU) and polyvinyl chloride (PVC). Amorphous polyethylene terephthalate (APET) and acrylonitrile-butadiene-styrene (ABS) are likewise suitable as a material for the inner layer. Since bacterial growth as well as permeation of pollutants may matter here, the inner layer will often have to be thicker than in the indoors application, since the thickness of the inner layer has a direct effect on the resistance to permeation. Layer thicknesses of from 0.2 to 0.6 mm are eligible for this purpose.

A third field of application is the use as a water mains pipe. The diameters of such pipes are often in the range of from 63 to 630 mm and possibly even larger. For this use too, both permeation and bacterial growth may matter, so that wall thicknesses of the inner layer of from 0.2 to 1.0 mm are desirable.

Experiments have shown that for the same layer thicknesses the permeability of PE to organic substances such as trichloroethylene, toluene, cyclohexanone and phenol is many thousand times larger than the permeability of PVC, PU, ABS and APET.

The table below gives an impression of the permeability ratios for the said substances, the permeability of PVC, PU, ABS and APET being defined as 1. In practice, this permeability will be even smaller.

Material	Trichloro-ethylene	Toluene	Cyclo-hexanone	Phenol
HDPE	100,000	5000	10,000	15,000
PVC	1	1	1	1
PU	1	1	1	1
ABS	1	1	1	1
APET	1	1	1	1

5

The experiments regarding bacterial growth have shown that in the case of PVC, CPVC, PU and APET under the same conditions the fouling by bacteria was smaller than in the case of PE by at least a factor of 20.

10

The following tables show examples of embodiments of water transmission tubes according to the invention in various fields of application. The material types PE 80 and PE 100 are PE types having different permitted wall stresses.

15

Tables with examples of tube types and their dimensions

D : nominal external diameter (mm)  
 E1 : nominal wall thickness of outer layer (mm)  
 E2 : nominal wall thickness of inner layer (mm)  
 M1 : material type of outer layer  
 M2 : material type of inner layer  
 PN : pressure class (bar)  
 S : tube class according to ISO 4065

20

1. TUBES FOR USE INDOORS

D	S	M1	E1	M2	E2
12	5	PEX/PB	1.3	PU/CPVC	0.1
16	5	PEX/PB	1.5	PU/CPVC	0.1
20	5	PEX/PB	1.9	PU/CPVC	0.1
25	5	PEX/PB	2.3	PU/CPVC	0.1

25

## 2. TUBES FOR USE OUTDOORS

D	PN	M1	E1	M2	E2
25	10	PE80	2.0	PU/PVC	0.2
32			2.4		0.2
40			3.0		0.2
50			3.7		0.2
63			4.7		0.3
75			5.6		0.3
110			8.1		0.5
160			11.8		0.6
200			14.7		0.8
250			18.4		1.0
315			23.2		1.0
400			29.4		1.0
500			36.8		1.0
630			46.3		1.0

D	PN	M1	E1	M2	E2
32	8	PE100	2.0	PU/PVC	0.6
40			2.0		0.6
50			2.4		0.6
63			3.0		0.6
75			3.6		0.6
110			5.3		0.6
160			7.7		0.6
200			9.6		0.6
250			11.9		0.6
315			15.0		0.8
400			19.1		1.0
500			23.9		1.0

- 6 -

CLAIMS

1. Water transmission tube made of a thermoplastic and having a wall comprising at least two layers, wherein the outer layer consists of a polyolefin material and the inner layer  
5 consists of a thermoplastic which is admixed only with substances required for processing it and which as such has no bacterial growth-promoting activity.
2. Water transmission tube according to claim 1, wherein the inner layer consists of a thermoplastic which is selected  
10 from the group consisting of polyvinyl chloride (PVC), chlorinated polyvinyl chloride (CPVC), thermoplastic polyurethane (PU), acrylonitrile-butadiene-styrene (ABS) and amorphous polyethylene terephthalate (APET).
3. Water transmission tube according to claim 1 or 2,  
15 wherein the inner layer is less permeable to organic substances than the outer layer.
4. Water transmission tube according to any one of claims 1-3, wherein the thickness of the inner layer is smaller by at least a factor of 3 than the thickness of the outer layer.
- 20 5. Water transmission tube according to any one of claims 1-4, wherein the inner layer has a thickness in the range of 0.1 - 1.0 mm.
6. Water transmission tube according to any one of claims 1-5, wherein a bonding layer is present between the inner layer  
25 and the outer layer.



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 99/00724

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 F16L9/133 F16L11/04 F16L11/12 F16L9/12

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 686 797 A (HUELS CHEMISCHE WERKE AG) 13 December 1995 (1995-12-13) cited in the application page 2, line 57 -page 3, line 51 page 5, line 49 - line 56; claim 17; tables 1,2	1-6
A	US 5 332 160 A (RUSKIN RODNEY R) 26 July 1994 (1994-07-26) cited in the application column 4, line 13-24	1-6
A	US 5 512 342 A (ROEBER STEFAN ET AL) 30 April 1996 (1996-04-30) abstract	1
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 February 2000

Date of mailing of the international search report

25/02/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Budtz-Olsen, A

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 99/00724

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 41 32 984 C (EGEPLAST) 12 November 1992 (1992-11-12) abstract ----	1
X	WO 97 30798 A (FERRALLI MICHAEL W) 28 August 1997 (1997-08-28) abstract ----	1
A	GB 2 296 303 A (EXTRUDIT LTD) 26 June 1996 (1996-06-26) ----	
A	US 5 510 160 A (JADAMUS HANS ET AL) 23 April 1996 (1996-04-23) ----	
A	DE 196 33 133 C (VERITAS GUMMIWERKE AG) 5 March 1998 (1998-03-05) -----	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 99/00724

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0686797	A	13-12-1995	DE 4418006 A BR 9502476 A CA 2149856 A DE 59500285 D ES 2103617 T JP 7314620 A NO 952005 A	23-11-1995 19-12-1995 22-11-1995 10-07-1997 16-09-1997 05-12-1995 22-11-1995
US 5332160	A	26-07-1994	WO 9513882 A AU 673728 B AU 6225994 A	26-05-1995 21-11-1996 06-06-1995
US 5512342	A	30-04-1996	DE 4336290 A BR 9400379 A CA 2114518 A DE 59406363 D EP 0649739 A ES 2118982 T JP 2644439 B JP 7117190 A	27-04-1995 20-06-1995 26-04-1995 06-08-1998 26-04-1995 01-10-1998 25-08-1997 09-05-1995
DE 4132984	C	12-11-1992	NONE	
WO 9730798	A	28-08-1997	US 5861191 A US 5894042 A CA 2247050 A EP 0885068 A	19-01-1999 13-04-1999 28-08-1997 23-12-1999
GB 2296303	A	26-06-1996	NONE	
US 5510160	A	23-04-1996	DE 4326130 A BR 9400381 A CA 2114517 A DE 59401887 D EP 0637511 A ES 2098800 T JP 2736219 B JP 7060916 A	09-02-1995 07-03-1995 05-02-1995 10-04-1997 08-02-1995 01-05-1997 02-04-1998 07-03-1995
DE 19633133	C	05-03-1998	FR 2752452 A	20-02-1998

**THIS PAGE BLANK (USPTO)**